

# SIA Ekobalta VG TECHNICAL TEXTILES

Vīksnes 29A-11, Rīga, LV-1069 tel. +371 29412054 email: [info@tehaudumi.lv](mailto:info@tehaudumi.lv) [www.tehaudumi.lv](http://www.tehaudumi.lv)

## Technical Data Sheet

### for industrial fabric: Arselon Fabric TTAB

**Yarn structure:**

100% arselon thread

Width in cm	80
Surface density (g/m <sup>2</sup> ) (weight per 1 m <sup>2</sup> )	480+/-20
Number of warp ends per 10 cm	120+/-10
Number of filling threads per 10 cm	110+/-5
Breaking strength of a 25 by 200 mm fabric strip (kgf) (warpwise) no less than	120
Breaking strength of a 25 by 200 mm fabric strip (kgf) (fillingwise) no less than	40
Stretch at break in % (fillingwise) not exceeding	5
Stretch at break in % (warpwise) not exceeding	5
Service temperature, °C	200-250

Air permeability, dm<sup>3</sup> / m<sup>2</sup>c

50+/-20

Rīga, 27.07.2023